

PRODUCT NAME	WOOD SPECIES	PRODUCT SPECIFICATION	CHARACTERISTIC	
PALEM PLYWOOD		MOISTURE CONTENT:		
		MAX 14%		
	FACE/BACK:	DENSITY:		
	MLH	- CORE FALCATA/RUBBER WOOD = 400-550 KG/CBM	- MULTI PURPOSE	
		- CORE FALCATA WOOD = 300-450 KG/CBM	- HIGH DIMENSIONAL STABILITY	
	CORE:	ADHESIVE:	- NATURAL WOOD APPEARANCE	
	FALCATA/RUBBER	T2 - UREA FORMALDEHYDE GLUE	- SUSTAINABLE WOOD PRODUCT	
	OR	T1 - MELAMINE UREA FORMALDEHYDE		
	FALCATA	FORMALDEHYDE EMISSION:		
		AVAILABLE:		
		- UP TO CARB PHASE 2/E0 FORMALDEHYDE EMISSION LEVEL		

SIZE DETAILS	THICKNESS (MM)	WIDTH (MM)	LENGTH (MM)	CONSTRUCTION
	2,7 MM	1220 MM (4')	2440 mm (8')	FROM 3 PLIES UP TO 9 PLIES DEPEND ON THICKNESS
	3,6 MM			
	5,0 MM			
	8,0 MM			
	9,0 MM			
	12,0 MM			
	15,0 MM			
	18,0 MM			

PACKING DETAILS	THICKNESS	DIMENSION (MM)	40' HC CONTAINER	
			NO. OF CRATES	NO. OF SHEETS
	2,7 MM	1220 MM X 2440 MM (4' X 8')	18	5850
	3,6 MM		18	4860
	5,0 MM		18	3960
	8,0 MM		18	2340
	9,0 MM		18	2250
	12,0 MM		18	1620
	15,0 MM		18	1314
	18,0 MM		18	1080

PRODUCT NAME	WOOD SPECIES	PRODUCT SPECIFICATION	CHARACTERISTIC
TUNAS PLYWOOD		MOISTURE CONTENT:	
		MAX 14%	
		DENSITY:	- UNIFORM COLOUR
		- CORE FALCATA WOOD = 300-400 KG/CBM	- LIGHTWEIGHT
	FACE/BACK:	ADHESIVE:	- GREAT INSULATOR
	FALCATA	T2 - UREA FORMALDEHYDE GLUE	- PROVIDE EXCELLENT SOUND DAMPING
	CORE:	T1 - MELAMINE UREA FORMALDEHYDE	- SUSTAINABLE WOOD PRODUCT
	FALCATA	FORMALDEHYDE EMISSION:	
		AVAILABLE:	
		- UP TO CARB PHASE 2/E0 FORMALDEHYDE EMISSION LEVEL	

SIZE DETAILS	THICKNESS (MM)	WIDTH (MM)	LENGTH (MM)	CONSTRUCTION
	2,7 MM	1220 MM (4')	2440 mm (8')	FROM 3 PLIES UP TO 9 PLIES DEPEND ON THICKNESS
	3,6 MM			
	5,0 MM			
	8,0 MM			
	9,0 MM			
	12,0 MM			
	15,0 MM			
	18,0 MM			

PACKING DETAILS	THICKNESS	DIMENSION (MM)	40' HC CONTAINER	
			NO. OF CRATES	NO. OF SHEETS
	2,7 MM	1220 MM X 2440 MM (4' X 8')	18	6480
	3,6 MM		18	4860
	5,0 MM		18	3780
	8,0 MM		18	2340
	9,0 MM		18	2250
	12,0 MM		18	1620
	15,0 MM		18	1314
	18,0 MM		18	1080

PRODUCT NAME	WOOD SPECIES	PRODUCT SPECIFICATION	CHARACTERISTIC
GMELINA PLYWOOD		MOISTURE CONTENT:	
		MAX 14%	
		DENSITY:	
	FACE/BACK:	- CORE MLH WOOD = 500-650 KG/CBM	- HIGH DIMENSIONAL STABILITY
	MLH	ADHESIVE:	- STRENGTH AND DURABILITY
	CORE:	T2 - UREA FORMALDEHYDE GLUE	- MINIMAL MOISTURE ABSORPTION
	MLH	T1 - MELAMINE UREA FORMALDEHYDE	- DENSE AND SHOCK RESISTANT
		FORMALDEHYDE EMISSION:	- NATURAL WOOD APPEARANCE
		AVAILABLE:	
		- UP TO CARB PHASE 2/E0/F4S FORMALDEHYDE EMISSION LEVEL	

SIZE DETAILS	THICKNESS (MM)	WIDTH (MM)	LENGTH (MM)	CONSTRUCTION
	2,7 MM	1220 MM (4') AVAILABLE FOR CUT SIZE	2440 mm (8') AVAILABLE FOR CUT SIZE	FROM 3 PLIES UP TO 7 PLIES DEPEND ON THICKNESS
	3,2 MM			
	3,6 MM			
	3,7 MM			
	5,0 MM			
	9,0 MM			
	12,0 MM			

PACKING DETAILS	THICKNESS	DIMENSION (MM)	40' HC CONTAINER	
			NO. OF CRATES	NO. OF SHEETS
	2,7 MM	1220 MM X 2440 MM (4' X 8')	16	5040
	3,2 MM		16	4000
	3,6 MM		16	3920
	3,7 MM		16	3680
	5,0 MM		16	2720
	9,0 MM		16	1600
	12,0 MM		16	1120

PRODUCT NAME	WOOD SPECIES	PRODUCT SPECIFICATION	CHARACTERISTIC
FORTUNA PLYWOOD		MOISTURE CONTENT:	
		MAX 14%	
		DENSITY:	
		- CORE RUBBER WOOD: 600-750 KG/CBM	- GOOD AT PROVIDING RIGIDITY FOR STRUCTURE
	FACE/BACK:	ADHESIVE:	- NOT PRONE TO WARPING AND SHRINKAGE AS OTHER MATERIAL TYPE
	MLH	T1 - PHENOLIC GLUE (WBP)	- LONG LASTING AND DURABLE
	CORE:	FORMALDEHYDE EMISSION:	- SUSTAINABLE WOOD PRODUCT
	RUBBER	AVAILABLE:	
		- UP TO E0 FORMALDEHYDE EMISSION LEVEL	

SIZE DETAILS	THICKNESS (MM)	WIDTH (MM)	LENGTH (MM)	CONSTRUCTION
	9,0 MM	UP TO 1250 MM (4')	UP TO 2500 MM (8')	FROM 7 PLIES UP TO 11 PLIES DEPEND ON THICKNESS
	12,0 MM			
	15,0 MM			
	18,0 MM			

PACKING DETAILS	THICKNESS	DIMENSION (MM)	40' HC CONTAINER	
			NO. OF CRATES	NO. OF SHEETS
	9,0 MM	UP TO 1250 MM X 2500 MM (4' X 8')	14	1400
	12,0 MM		14	980
	15,0 MM		14	840
	18,0 MM		14	700

PRODUCT NAME	WOOD SPECIES	PRODUCT SPECIFICATION	CHARACTERISTIC
GP PALEM		MOISTURE CONTENT:	
		MAX 14%	
		DENSITY:	- SMOOTH SURFACE
	FACE/BACK:	- CORE FALCATA WOOD = 300-450 KG/CBM	- MULTI PURPOSE
	MLH	ADHESIVE:	- HIGH DIMENSIONAL STABILITY
	CORE:	T2 - UREA FORMALDEHYDE GLUE	- NATURAL WOOD APPEARANCE
	FALCATA	T1 - MELAMINE UREA FORMALDEHYDE GLUE	- SUSTAINABLE WOOD PRODUCT
		FORMALDEHYDE EMISSION:	
		AVAILABLE:	
		- UP TO JAS F☆☆☆☆ FORMALDEHYDE EMISSION LEVEL	

SIZE DETAILS	THICKNESS (MM)	WIDTH (MM)	LENGTH (MM)	CONSTRUCTION
	3,7 MM	910 MM / 915 MM / 920 MM (3')	1820 MM /1830 MM (6')	FROM 3 PLIES UP TO 9 PLIES DEPEND ON THICKNESS
	5,2 MM			
	8,6 MM			
	11,6 MM			
	14,6 MM			
	17,6 MM			

PACKING DETAILS	THICKNESS	DIMENSION (MM)	40' HC CONTAINER	
			NO. OF CRATES	NO. OF SHEETS
	3,7 MM	910 MM / 915 MM / 920 MM X 1820 MM / 1830 mm (3' X 6')	24	6600
	5,2 MM		24	5160
	8,6 MM		24	3000
	11,6 MM		24	2280
	14,6 MM		24	1776
	17,6 MM		24	1440

PRODUCT NAME	WOOD SPECIES	PRODUCT SPECIFICATION		CHARACTERISTIC	
GP TUNAS		MOISTURE CONTENT:			
		MAX 14%			
		DENSITY:		- SMOOTH SURFACE	
	FACE/BACK:	- CORE FALCATA WOOD = 300-400 KG/CBM		- UNIFORM COLOUR	
	FALCATA	ADHESIVE:		- LIGHTWEIGHT	
	CORE:	T2 - UREA FORMALDEHYDE GLUE		- GREAT INSULATOR	
	FALCATA	T1 - MELAMINE UREA FORMALDEHYDE		- PROVIDE EXCELLENT SOUND DAMPING	
		FORMALDEHYDE EMISSION:		- SUSTAINABLE WOOD PRODUCT	
		AVAILABLE:			
	- UP TO JAS F☆☆☆☆ FORMALDEHYDE EMISSION LEVEL				
SIZE DETAILS		THICKNESS (MM)	WIDTH (MM)	LENGTH (MM)	CONSTRUCTION
		8,6 MM	910 MM / 915 MM / 920 MM (3')	1820 MM / 1830 MM (6')	FROM 5 PLIES UP TO 7 PLIES DEPEND ON THICKNESS
		11,6 MM			
PACKING DETAILS		THICKNESS	DIMENSION (MM)	40' HC CONTAINER	
				NO. OF CRATES	NO. OF SHEETS
		8,6 MM	910 MM / 915 MM / 920 MM X 1820 MM / 1830 mm (3' X 6')	24	3000
		11,6 MM		24	2280