PRODUCT NAME	WOOD SPECIES	PRODUCT SPECIFICATION	CHARACTERISTIC
LVL	RUBBER WOOD, MLH OR FALCATA WOOD (CAN BE MIX SUBJECT TO REQUIREMENT)	MOISTURE CONTENT:	
		MAX 14%	
		DENSITY:	
		- CORE FALCATA: 250-350 KG/CBM	
		- CORE RUBBER WOOD: 500-650 KG/CBM	
		- CORE MLH: 500-650 KG/CBM	
		VENEER THICKNESS:	
		- 1.7 MM AND 2.5 MM	- EXCELLENT DURABILITY
		ADHESIVE:	- DIMENSIONALLY STABLE
		T2 - UREA FORMALDEHYDE GLUE	- UNIFORM STRUCTURE
		T1 - PHENOLIC GLUE (WBP)	- EASY TO INSTALL
		FORMALDEHYDE EMISSION:	- SUSTAINABLE SUPPLY
		AVAILABLE:	
		- UP TO E0/F★★★★ FORMALDEHYDE EMISSION LEVEL	
		FINISHING:	
		- SANDED/UNSANDED SURFACE	
		- CUSTOMIZED PANEL SIZE	
		- CUT TO SIZE	
		- EDGE PROFILING	

	THICKNESS (MM)	WIDTH (MM)	LENGTH (MM)	CONSTRUCTION
SIZE DETAILS	40 MM UNTIL 100 MM	40 MM UNTIL 500 MM	MAX 5000 MM	DEPEND ON THICKNESS
SIZE DETAILS	25 MM UNTIL 50 MM	400 MM UNTIL 1220 MM	MAX 2500 MM	
	15 MM UNTIL 50 MM	1220 MM	MAX 2500 MM	